



Product Information

Nasiol ZR53 is a nano ceramic coating for car body paint, lights, black plastics and trim surfaces which protects your car against scratches, bird droppings, acid rains, UV irradiation, detergents and several chemicals ZR 53 is the ultimate nano ceramic vehicle protection product that brings a hydrophobic effect in a single layer of coating to applied surfaces listed below:

Application Surfaces

Car body paint, lights, black plastic, trim surfaces. Don't use on chromated and unlacquered painted plastic parts.

Instructions

- Surfaces should be dry and free of any dust, wax, oil, grease and other contamination.
- Prepare the surface by using Nasiol Clean to improve the bonding performance of the nano coating.
- Place a suede cloth onto the applicator block's sponge surface.
- Open the lid and pour the necessary amount of product onto the suede cloth.
- Spread the product gently over the surface in a crisscross motion.
- Once beading occurs (it takes 30 seconds in normal conditions), gently wipe the excess product off from the surface using the Nasiol microfiber cloth in linear motions.
- Keep the coated surfaces away from direct sunlight, the elements, various types of contamination, and water exposure for 24 hours.

Application Tips

Nasiol ZR53 has been developed for both end users and professionals. Application to a mid-size car takes 60 - 90 minutes. Ensure that the temperature and relative humidity (RH) values (+5 °C ~ + 30 °C / 41 F ~ 86 F / 50% RH) of the application space are as close as possible to suggested condition in order to obtain maximum product performance.

If the ambient temperature or relative humidity value is higher than suggested intervals / values, the product may cure faster than expected. Avoid direct

sunlight during the application and only work on cool surfaces.

Wash your vehicle thoroughly. If required, apply clay bar. After decontamination, apply polishing / compounding with appropriate tools and silicone / wax-free cutting compounds in accordance with the physical condition of your vehicle's surface. When polishing is complete, wash the vehicle and ensure that all the application areas are thoroughly dry. A compressed air gun may be used to eliminate the risk of water dripping from trims and joints.

Prepare the surface by using Nasiol Clean to improve the bonding performance of the nano coating. Ensure that there isn't any residual contamination and dry the surface with a lint-free microfiber cloth. Do not work on areas larger than 1 m² per session.

Before using the product, wear the protective nitrile gloves included in the box. Place a suede cloth onto the applicator block's sponge surface.

Change the suede cloth every 3-4 panels. Shake the product gently before use. Open the lid and pour the necessary amount of product onto the suede cloth. 4-5 mL is enough for 1 m² area.

Do not forget to keep the lid closed during the application. Spread the product gently over the surface in a crisscross motion. Once beading occurs (it takes 30 seconds in normal conditions), gently wipe the excess product off from the surface using the Nasiol microfiber cloth in linear motions. To make the most of microfiber cloths, fold each one four times before application and do not re-use the side of the cloth you used. If it is too late for the first wiping step, the product may cure on the surface, making wiping harder or even impossible. In that



Technical Data Sheet

ZR53

case, the product should be removed from the surface by polishing or sanding.

After correction, the product should be re-applied properly. After wiping the surface with the microfiber cloth, complete the final buffing process by gently using the Nasiol microfiber cloth in circular motions.

Keep the coated surfaces away from direct sunlight, the elements, various types of contamination, and water exposure for 24 hours. Please wait 48 hours for the nano coating to cure and become resistant to abrasion and chemicals, before any detergent-based washing.

Benefits & Key Features

- High Hydrophobicity
- High Chemical Resistance
- Soft Touch with Suede Cloth
- Matchless Gloss Effect
- Crystal Gloss
- 10H Scratch Resistance
- Ergonomic Applicator Block

Specifications

| | |
|--|------------------------|
| Packaging | 50 mL |
| Appearance | Colorless liquid |
| Durability | Up to 3 years |
| Chemical Resistance | 12>pH>1 |
| Salt Water Resistance | Yes |
| Moisture Resistance | Yes |
| Pencil Hardness (ISO-15184:2012) | 10H |
| Dry Film Thickness | 700-800 nm |
| Consumption per Unit Area | 4-5 mL/m ² |
| Density @23°C | 0.86 g/cm ³ |
| pH Value | 5-5.5 |
| Dry to Touch Time | 4h |
| Application Temperature | 5°C-30°C (≤50%RH) |
| Temperature Durability | 150°C |
| Water Contact Angle | 105° @10 µL |
| Water Contact Angle After "3000 Wet Scrub (ISO-11998:2006) | 100° @10 µL |

| | |
|------------------------------------|--------------|
| Water Sliding Angle | 11° @20 µL |
| Oil Contact Angle | 84° @10 µL |
| Gloss Rate @60° (ISO-2813:2014) | 95 (Acrylic) |
| REACH Compliance | Yes |

Consumption

| | |
|--------------------------------|----------|
| Small Vehicles (A-B Class) | 30-35 mL |
| Medium Vehicles (C-D Class) | 35-40 mL |
| Large Vehicles (E Class & SUV) | 40-50 mL |

Recommended Cloth Specifications

| | |
|--------|-------------------------------------|
| Model | Nasiol Microfiber Clothes |
| Blend | 70-80% Polyamide & 20-30% Polyester |
| Weight | 250-350 gsm |

Storage

To achieve a high product effectiveness, keep the unopened packaging in a dry, well ventilated space away from heat and ignition sources, stored at -3 °C to + 30°C / 26.60 °F to 86 °F. The shelf life of product is 24 months from the date of production when stored in the unopened packaging under suggested storage conditions. After opening the container, it is recommended to use the product within 1 week. After every use, it is recommended to close the lid in order to avoid product loss by evaporation.

Disclaimer

The technical information described in this document is based on tests and other practical experience that Nasiol believes are reliable. Nasiol cannot guarantee anything but ready to use quality of the product at the time of shipment, disclaims any liability for product performance and incidental or consequential damages, according to self-implementation within the user's knowledge, beyond the manufacturer's control. Please refer to the Safety Data Sheet (SDS) before use of product.

Users should consult Nasiol for guidance on the suitability of specific applications. Nasiol reserves the right to change the given data without further notice.